



ANTI-CONDENSATION 12 MIL GREENHOUSE FILM

CLEAR GREENHOUSE MATERIAL WITH ANTI-CONDENSATE & SULPHUR RESISTANCE.

TECHNICAL SPECIFICATIONS PRODUCT DATA SHEET

PROPERTY	TEST METHOD	TEST RESULT
FABRICATION & WAREHOUSE		PRINEVILLE, OR
WEIGHT		6oz./sq.yd. (+/-5%)
THICKNESS		12 MILS (+/-10%)
COATING THICKNESS		1.75 MILS EACH (+/-10%)
TENSILE STRENGTH (GRAB METHOD)	ASTM D 5034	WARP 220 LBS WEFT 175 LBS.
TEAR STRENGTH (TONGUE METHOD)	ASTM D 2261	WARP 65 LBS/INCH WEFT 65 LBS/INCH
BURSTING STRENGTH (MULLEN)	ASTM D 3786	370 PSI
UV RESISTANCE	ASTM G-151	>80% STRENGTH RETAINED AFTER 2000 HRS
LIGHT TRANSMITTANCE	ASTM D 1003	NIR 75% Visible 82% Diffusion/Haze 82%

FILM IS LOW TEMPERATURE - HYDROCARBON STABLE, AND COATED ON BOTH SIDES WITH HIGH UV STABILIZED LDPE COATING. ALL DATA IS DRAWN FROM U.S. TESTING AND PRECISION LABORATORIES. AVAILABLE ON REQUEST

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty, warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.